# Heavy Conveyor Belts APH120FBS-E3




# Main industry segments

Airport, Distribution centers, Parcel distribution / Overnight carrier

# **Special features**

Energy saving, Flame retardant, High strength





Product Construction / Design	
Conveying side material	Polyester fabric (PET) impregnated with polyvinylchloride (PVC)
Conveying side surface	Fabric
Conveying side property	Non-adhesive
Conveying side color	Black
Traction layer (material)	Polyester (PET)
Number of Fabrics	1
Pulley side material	Polyester (PET)
Pulley side surface	Impregnated fabric
Pulley side property	Non-adhesive
Pulley side color	Green

Product characteristics					
Antistatically equipped	No				
Adhesive free joining method	Yes				
Flammability	Flame retardant, Flame retardant to ASTM D-378				
Food suitability, FDA conformance	No				
Food suitability, USDA recommendations	No use intended				
Food suitability, EU conformance	No				

# Heavy Conveyor Belts APH120FBS-E3



Technical data							
Thickness of belt	3.6	mm	0.14	inch			
Mass of belt (belt weight)	3.4	kg/m²	0.690	lb/sqft			
Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155)	36	N/mm	206	lbf/in			
Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181)	12	N/mm	69	lbf/in			
Min. operating temperature admissible (continuous)	-18	°C	0	°F			
Max. operating temperature admissible (continuous)	82	°C	180	°F			
Coefficient of friction (pulley side / steel driving pulley)	0.15	-					
Coefficient of friction (pulley side / driving pulley with friction cover)	0.25	-					
Coefficient of friction (pulley side / pickled steel slider bed)	0.20	-					
Seamless manufacturing width	1829	mm	72.00	inch			
On request other seamless manufacturing width	1524	mm	60	inch			

## Joining related properties

Joining method			
Clipper #2HT	Master joining method for standard applications		
Flexproof 10 x 80	Optional joining method		
Thermofix	Optional joining method		

## Link to JDS:

Joining method		Clipper #2HT	Flexproof 10 x 80	Thermofix
Pulley diameter (minimum)	mm	79	76	76
	inch	3.10	3.00	3.00
Pulley diameter minimum with	mm	79	76	76
counter flection	inch	3.10	3.00	3.00
Admissible tensile force per unit of	N/mm	21		
width	lbf/in	120		
Admissible tensile force per unit of	N/mm	6.7		
width at max. operating	lbf/in	38		
temperature				
Slider bed suitable		Yes	Yes	Yes
Carrying rollers suitable		Yes	Yes	Yes
Troughed installation suitable		No	No	
Powerturns / curved installations		No	No	
Knife-edge (nosebar) suitable		No	No	
Low noise applications		No	No	No
Metal detector suitable		No	No	No

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554). Limited representative testing based on a standard configuration is carried out to estimate minimum pulley diameters. Please contact Habasit for specific guidance regarding non-standard applications, including, but not exclusively, when profiles or cleats are used, or if the belt working temperature is close to the limits listed in this document.

# Heavy Conveyor Belts APH120FBS-F3



### Chemical resistance

Link to 'Chemical resistance information': https://rims.habasit.com

### Mode of use or conveyance

Diverting, Horizontal

### **Calculations**

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

## Recommendation

Do not go below initial elongation (epsilon) ~ 0.5%, Install the slack belt and tension until running perfectly under the full belt load

Protect belts from sunlight/UV-radiation/dust and dirt. Store spare belts in a cool and dry place and if possible in their original packaging. Check Link for Storage requirements:

"https://tdm.habasit.com/pds/en-us/Storage%20of%20Habasit%20material.pdf"

No danger and limitation

Group Woven PVC Belts Sub-Group **Energy Saving Belts** Item number H250000256

Disclaimer
Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)
This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not precessarily match product performance in industrial use. New knowledge and experience may lead to accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice.

EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.