Michigan Industrial Belting Inc.
31617 Glendale St.
Livonia, MI 48150
We have years of experience and service under our belts.

Phone: 734-427-7700
Fax: 734-427-0788
Est 1978

MIB133D

Catalog # **133D**
Item number: **32079**
Description:
2 Ply Poly 69 Black PVC ID AS FR
International Designation:
EM12/2 0/V6 Black ID AS FR

Construction:

Compound Top Cover	Black PVC
Top Cover Thickness (in)	(0.60 mm) 0.0236 in
Top Cover Description	Inverted Drop
Top Cover Shore	35
Compound Bottom Cover	Polyester
Bottom Cover Thickness (in)	(0.00 mm) 0.0000 in
Bottom Cover Description	Bare
Bottom Cover Shore	N/A
Number of Plies	2
Anti Static	Yes
Overall Gauge (in)	(2.60 mm) 0.1024 in
Unit Weight- lb/PIW	0.0495 lbs/PIW
Material Between Plies	PVC
Maximum Width (in)	102 in
Temperature Range (°F)- High	176 °F
Temperature Range (°F)- Low	-4 °F

Pulley Diameter, Minimum



A) Normal Flex	(50.00 mm) 1.9685 in
B) Back Flex	(75.00 mm) 2.9528 in

Belt Strength:

Pull for 1% Elongation	(12 N/mm) 69 lbs/sq in

Splice Instructions:

Foil	Yes
Splice Process	Finger
Press Temperature (°F)	330 °F
Press Pressure (psi)	25 lbs/sq in

Note: Listed above is a guideline only. Every vulcanizer is different and will show different results. We recommend that you do a test splice with your press before attempting the actual belt splice.

Other:

Cross Rigid	No
Impression Top	Yes
Oil Resistant	No
Fire Resistant	Yes
FDA Approved	No

Special Characteristics:
N/A

*****All Values are nominal and subject to change without notice.*****