Michigan Industrial Belting Inc.
31617 Glendale St.
Livonia, MI 48150
We have years of experience and service under our belts.

Phone: 734-427-7700
Fax: 734-427-0788
Est 1978

MIB139a

Catalog #	**139a**
Item number:	**24230**

Description:
NW 25 Black HC

International Designation:
NW 25 HC SF Black

Construction:

Compound Top Cover	Polyester Fleece
Top Cover Thickness (in)	(0.00 mm) 0.0000 in
Top Cover Description	Smooth
Top Cover Shore	N/A
Compound Bottom Cover	Polyester Fleece
Bottom Cover Thickness (in)	(0.00 mm) 0.0000 in
Bottom Cover Description	Non-Woven
Bottom Cover Shore	N/A
Number of Plies	1
Anti Static	Yes
Overall Gauge (in)	(2.60 mm) 0.1024 in
Unit Weight- lb/PIW	0.0290 lbs/PIW
Material Between Plies	N/A
Maximum Width (in)	79 in
Temperature Range (°F)- High	250 °F
Temperature Range (°F)- Low	14 °F

Pulley Diameter, Minimum



A) Normal Flex	(38.10 mm) 1.5000 in
B) Back Flex	(38.10 mm) 1.5000 in

Belt Strength:

Pull for 1% Elongation	(15 N/mm) 85 lbs/sq in

Splice Instructions:

Foil	No
Splice Process	Skive
Press Temperature (°F)	180 °F
Press Pressure (psi)	18 lbs/sq in

Note: Listed above is a guideline only. Every vulcanizer is different and will show different results. We recommend that you do a test splice with your press before attempting the actual belt splice.

Other:

Cross Rigid	No
Impression Top	No
Oil Resistant	Yes
Fire Resistant	No
FDA Approved	No

Special Characteristics:

This belt is manufactured with a nonwoven construction that is highly conductive, wear and cut resistant, quiet running and offers a soft impact surface. Commonly used in automotive applications, mail and post sorting systems, airport luggage handling and distributions centers. This belt resembles a felt like construction suitable for conveying plastic parts or electronic components.

*****All Values are nominal and subject to change without notice.*****