Michigan Industrial Belting Inc.
31617 Glendale St.
Livonia, MI 48150
We have years of experience and service under our belts.

Phone: 734-427-7700
Fax: 734-427-0788
Est 1978

MIB140BBS

Catalog #	**140BBS**
Item number:	**49989**

Description:
NW 150 Black RMV FxF FR

International Designation:
ENW 26/1 RMV0/RMV0 Black FR

Construction:

Compound Top Cover	Black Rubber Mod. Vinyl (RMV)
Top Cover Thickness (in)	(0.00 mm) 0.0000 in
Top Cover Description	Impregnated Fleece
Top Cover Shore	N/A
Compound Bottom Cover	Black Rubber Mod. Vinyl (RMV)
Bottom Cover Thickness (in)	(0.00 mm) 0.0000 in
Bottom Cover Description	Impregnated Fleece
Bottom Cover Shore	N/A
Number of Plies	1
Anti Static	Yes
Overall Gauge (in)	(3.70 mm) 0.1457 in
Unit Weight- lb/PIW	0.0529 lbs/PIW
Material Between Plies	N/A
Maximum Width (in)	72 in
Temperature Range (°F)- High	160 °F
Temperature Range (°F)- Low	0 °F

Pulley Diameter, Minimum



A) Normal Flex	(50.80 mm) 2.0000 in
B) Back Flex	(50.80 mm) 2.0000 in

Belt Strength:

Pull for 1% Elongation	(26 N/mm) 150 lbs/sq in

Splice Instructions:

Foil	Yes
Splice Process	Finger
Press Temperature (°F)	356 °F
Press Pressure (psi)	19 lbs/sq in

Note: Listed above is a guideline only. Every vulcanizer is different and will show different results. We recommend that you do a test splice with your press before attempting the actual belt splice.

Other:

Cross Rigid	No
Impression Top	No
Oil Resistant	Yes
Fire Resistant	Yes
FDA Approved	No

Special Characteristics:

The 140BBS is commonly used in logistics applications. The rugged non-woven construction has excellent fastener retention qualities and the RMV impregnation of the fabric gives the belt additional oil resistance when compared to PVC.

*****All Values are nominal and subject to change without notice.*****