



# Michigan Industrial Belting Inc.

31617 Glendale St.  
Livonia, MI 48150

*We have years of experience and service under our belts.*

Phone: 734-427-7700


Fax: 734-427-0788



Est 1978

## MIB-2B15

<b>Catalog #</b>	<b>2B15</b>
<b>Item number:</b>	<b>41885</b>
<b>Description:</b>	IWP 140 3/32in Red Urethane X FS
<b>International Designation:</b>	EM24/M UO/U24 Red

<b>Pulley Diameter, Minimum</b>	
	
A) Normal Flex	(100.00 mm) 3.9370 in
B) Back Flex	(200.00 mm) 7.8740 in

<b>Construction:</b>	
Compound Top Cover	Red PU
Top Cover Thickness (in)	(2.40 mm) 0.0945 in
Top Cover Description	Gloss
Top Cover Shore	92
Compound Bottom Cover	Solid Woven
Bottom Cover Thickness (in)	(0.00 mm) 0.0000 in
Bottom Cover Description	Friction Surface
Bottom Cover Shore	N/A
Number of Plies	1
Anti Static	No
Overall Gauge (in)	(5.00 mm) 0.1969 in
Unit Weight- lb/PIW	0.0916 lbs/PIW
Material Between Plies	PU
Maximum Width (in)	118 in
Temperature Range (°F)- High	176 °F
Temperature Range (°F)- Low	5 °F

<b>Belt Strength:</b>	
Pull for 1% Elongation	(25 N/mm) 140 lbs/sq in

<b>Splice Instructions:</b>	
Foil	Yes
Splice Process	Finger
Press Temperature (°F)	320 °F
Press Pressure (psi)	25 lbs/sq in
Note: Listed above is a guideline only. Every vulcanizer is different and will show different results. We recommend that you do a test splice with your press before attempting the actual belt splice.	

<b>Other:</b>	
Cross Rigid	No
Impression Top	No
Oil Resistant	Yes
Fire Resistant	No
FDA Approved	No

**Special Characteristics:**  
The 2B15 is an excellent choice for tough applications found in recycling and metal stamping plants. The 92 Shore A PU cover is cut and gouge resistant.

\*\*\*\*\*All Values are nominal and subject to change without notice.\*\*\*\*\*