



Michigan Industrial Belting Inc.

31617 Glendale St.
Livonia, MI 48150

Phone: 734-427-7700

Fax: 734-427-0788



Est 1978

We have years of experience and service under our belts.

MIB75a

| | |
|-----------------------------------|----------------------------|
| Catalog # | 75a |
| Item number: | 10468 |
| Description: | 3 Ply 225 1/8in x Bare MOR |
| International Designation: | N/A |

| | |
|--|----------|
| Pulley Diameter, Minimum | |
| Min. Pulley Dia. - Head @ 80 - 100% Tension | 16.00 in |
| Min. Pulley Dia. - Head @ 60 - 79% Tension | 14.00 in |
| Min. Pulley Dia. - Head @ 59% Tension or Below | 10.00 in |
| Minimum Pulley Diameter- Tail | 10.00 in |

| | |
|------------------------------|-------------------|
| Construction: | |
| Compound Top Cover | Black MOR |
| Color | Black |
| Top Cover Thickness (in) | (3.30 mm) 1/8 in |
| Top Cover Description | Smooth |
| Compound Bottom Cover | Poly/Nylon |
| Bottom Cover Thickness (in) | (0.00 mm) 0.00 in |
| Bottom Cover Description | Bare |
| Number of Plies | 3 |
| Overall Gauge (in) | (6.35 mm) 1/4 in |
| Unit Weight- lb/PIW | 0.1560 lbs/PIW |
| Carcass Type | Poly/Nylon |
| Compound | Black MOR |
| Temperature Range (°F)- High | 225 °F |
| Temperature Range (°F)- Low | -25 °F |

| | |
|-----------------------------|----------|
| Splice Instructions: | |
| Splice Step Size | 8.00 in |
| Splice Process | Step Hot |

| | |
|-------------------|-----|
| Other: | |
| Static Conducting | No |
| Cross Rigid | No |
| High Heat | No |
| Impression Top | No |
| Oil Resistant | Yes |
| Fire Resistant | No |
| FDA Approved | No |

| | |
|-----------------------|---------|
| Belt Strength: | |
| Tension Rating (PIW) | 225 PIW |

| | |
|-----------------------------|-------------|
| Suggested Fasteners: | |
| Flexco Plate/Rivet | #140/R5 |
| Flexco Hinged | #375 or 550 |
| Alligator Staple | N/A |
| Clipper Lace | N/A |
| Alligator Lace | N/A |

Special Characteristics:
 This belt features a high-strength 3 ply polyester carcass. Also used for heavier applications needing a tough cover with a low-friction bottom. Moderately oil resistant for processing wood chips, paper and scrap.

*****All Values are nominal and subject to change without notice.*****