



# Michigan Industrial Belting Inc.

31617 Glendale St.  
Livonia, MI 48150

*We have years of experience and service under our belts.*

Phone: 734-427-7700

Fax: 734-427-0788



Est 1978

## MIB79a

<p><b>Catalog #</b>                    <b>79a</b></p> <p><b>Item number:</b>                <b>41332</b></p> <p><b>Description:</b> 3 Ply 330 Tan Pure Gum 13/64in x Bare</p> <p><b>International Designation:</b> N/A</p>	<p><b>Pulley Diameter, Minimum</b></p> <table> <tr> <td>Min. Pulley Dia. - Head @ 80 - 100% Tension</td> <td>16.00 in</td> </tr> <tr> <td>Min. Pulley Dia. - Head @ 60 - 79% Tension</td> <td>14.00 in</td> </tr> <tr> <td>Min. Pulley Dia. - Head @ 59% Tension or Below</td> <td>10.00 in</td> </tr> <tr> <td>Minimum Pulley Diameter- Tail</td> <td>10.00 in</td> </tr> </table>	Min. Pulley Dia. - Head @ 80 - 100% Tension	16.00 in	Min. Pulley Dia. - Head @ 60 - 79% Tension	14.00 in	Min. Pulley Dia. - Head @ 59% Tension or Below	10.00 in	Minimum Pulley Diameter- Tail	10.00 in																								
Min. Pulley Dia. - Head @ 80 - 100% Tension	16.00 in																																
Min. Pulley Dia. - Head @ 60 - 79% Tension	14.00 in																																
Min. Pulley Dia. - Head @ 59% Tension or Below	10.00 in																																
Minimum Pulley Diameter- Tail	10.00 in																																
<p><b>Construction:</b></p> <table> <tr> <td>Compound Top Cover</td> <td>Tan NR</td> </tr> <tr> <td>Color</td> <td>Tan</td> </tr> <tr> <td>Top Cover Thickness (in)</td> <td>(5.46 mm) 13/64 in</td> </tr> <tr> <td>Top Cover Description</td> <td>Puregum</td> </tr> <tr> <td>Compound Bottom Cover</td> <td>Poly/Nylon</td> </tr> <tr> <td>Bottom Cover Thickness (in)</td> <td>(0.00 mm) 0.00 in</td> </tr> <tr> <td>Bottom Cover Description</td> <td>Bare</td> </tr> <tr> <td>Number of Plies</td> <td>3</td> </tr> <tr> <td>Overall Gauge (in)</td> <td>(9.92 mm) 3/8 in</td> </tr> <tr> <td>Unit Weight- lb/PIW</td> <td>0.1750 lbs/PIW</td> </tr> <tr> <td>Carcass Type</td> <td>Poly/Nylon</td> </tr> <tr> <td>Compound</td> <td>Tan NR</td> </tr> <tr> <td>Temperature Range (°F)- High</td> <td>225 °F</td> </tr> <tr> <td>Temperature Range (°F)- Low</td> <td>-20 °F</td> </tr> </table>	Compound Top Cover	Tan NR	Color	Tan	Top Cover Thickness (in)	(5.46 mm) 13/64 in	Top Cover Description	Puregum	Compound Bottom Cover	Poly/Nylon	Bottom Cover Thickness (in)	(0.00 mm) 0.00 in	Bottom Cover Description	Bare	Number of Plies	3	Overall Gauge (in)	(9.92 mm) 3/8 in	Unit Weight- lb/PIW	0.1750 lbs/PIW	Carcass Type	Poly/Nylon	Compound	Tan NR	Temperature Range (°F)- High	225 °F	Temperature Range (°F)- Low	-20 °F	<p><b>Splice Instructions:</b></p> <table> <tr> <td>Splice Step Size</td> <td>8.00 in</td> </tr> <tr> <td>Splice Process</td> <td>Step Hot</td> </tr> </table>	Splice Step Size	8.00 in	Splice Process	Step Hot
Compound Top Cover	Tan NR																																
Color	Tan																																
Top Cover Thickness (in)	(5.46 mm) 13/64 in																																
Top Cover Description	Puregum																																
Compound Bottom Cover	Poly/Nylon																																
Bottom Cover Thickness (in)	(0.00 mm) 0.00 in																																
Bottom Cover Description	Bare																																
Number of Plies	3																																
Overall Gauge (in)	(9.92 mm) 3/8 in																																
Unit Weight- lb/PIW	0.1750 lbs/PIW																																
Carcass Type	Poly/Nylon																																
Compound	Tan NR																																
Temperature Range (°F)- High	225 °F																																
Temperature Range (°F)- Low	-20 °F																																
Splice Step Size	8.00 in																																
Splice Process	Step Hot																																
<p><b>Belt Strength:</b></p> <table> <tr> <td>Tension Rating (PIW)</td> <td>330 PIW</td> </tr> </table>	Tension Rating (PIW)	330 PIW	<p><b>Other:</b></p> <table> <tr> <td>Static Conducting</td> <td>No</td> </tr> <tr> <td>Cross Rigid</td> <td>No</td> </tr> <tr> <td>High Heat</td> <td>No</td> </tr> <tr> <td>Impression Top</td> <td>No</td> </tr> <tr> <td>Oil Resistant</td> <td>No</td> </tr> <tr> <td>Fire Resistant</td> <td>No</td> </tr> <tr> <td>FDA Approved</td> <td>No</td> </tr> </table>	Static Conducting	No	Cross Rigid	No	High Heat	No	Impression Top	No	Oil Resistant	No	Fire Resistant	No	FDA Approved	No																
Tension Rating (PIW)	330 PIW																																
Static Conducting	No																																
Cross Rigid	No																																
High Heat	No																																
Impression Top	No																																
Oil Resistant	No																																
Fire Resistant	No																																
FDA Approved	No																																
<p><b>Special Characteristics:</b></p> <p>Popularly used in the lumber industry as a slow down belt. This is a versatile belt that can be used in temperatures ranging from -20 degrees F to 225 degrees F (intermittent).</p>	<p><b>Suggested Fasteners:</b></p> <table> <tr> <td>Flexco Plate/Rivet</td> <td>#140/R5</td> </tr> <tr> <td>Flexco Hinged</td> <td>N/A</td> </tr> <tr> <td>Alligator Staple</td> <td>N/A</td> </tr> <tr> <td>Clipper Lace</td> <td>N/A</td> </tr> <tr> <td>Alligator Lace</td> <td>N/A</td> </tr> </table>	Flexco Plate/Rivet	#140/R5	Flexco Hinged	N/A	Alligator Staple	N/A	Clipper Lace	N/A	Alligator Lace	N/A																						
Flexco Plate/Rivet	#140/R5																																
Flexco Hinged	N/A																																
Alligator Staple	N/A																																
Clipper Lace	N/A																																
Alligator Lace	N/A																																
<p>*****All Values are nominal and subject to change without notice.*****</p>																																	